



Evolution Fasteners (UK) Ltd
 Units 2A & 2B Clyde Gateway Trade Park
 Dalmarnock Road, Rutherglen, Glasgow G73 1AN
 Tel: +44 (0)141 647 7100 / Fax: +44 (0)141 647 5100
 Email: technical@evolutionfasteners.co.uk



www.evolutionfasteners.co.uk



PRODUCT DATASHEET

BI-METAL WING-DRILL TEK SCREW

Product Details

Designed for: *Fastening when stainless steel product is required e.g. in conjunction with aluminium sheeting/ panels and steel substrates*

Head style: *Countersunk*

Drive bit: *Phillips 3*

Thread form: *Twin, coarse thread (Tek 3)/fine thread (Tek 5)*

Shank material: *Stainless steel*

Material grade: *AISI A304*

Coating: *Electroplated zinc*



Bi-metal wing drill tek screw range – for light steel

Product Code	Size	Drill point	Effective thread length	Drilling Capacity	Recommended drill speed	Timber thickness
BMWD4.8-38-3	4.8x38mm	Tek 3	24.0mm	1.2 – 4.0mm	1500-2500 RPM	6.0 – 22.0mm
BMWD5.5-50-3	5.5x50mm	Tek 3	FULL	1.2 – 4.0mm	1500-2500 RPM	13.0 – 30.0mm
BMWD5.5-62-3	5.5x62mm	Tek 3	40.0mm	1.2 – 4.0mm	1500-2500 RPM	13.0 – 40.0mm
BMWD5.5-80-3	5.5x80mm	Tek 3	60.0mm	1.2 – 4.0mm	1500-2500 RPM	25.0 – 60.0mm
BMWD5.5-100-3	5.5x100mm	Tek 3	60.0mm	1.2 – 4.0mm	1500-2500 RPM	45.0 – 80.0mm
BMWD5.5-120-3	5.5x120mm	Tek 3	60.0mm	1.2 – 4.0mm	1500-2500 RPM	45.0 – 100.0mm

Bi-metal wing drill tek screw range– for heavy steel

Product Code	Size	Drill point	Effective thread length	Drilling Capacity	Recommended drill speed	Timber thickness
BMWD5.5-65-5	5.5x65mm	Tek 5	FULL	4.0 – 12.5mm	1500-2500 RPM	10.0 – 28.0mm
BMWD5.5-85-5	5.5x85mm	Tek 5	50.0mm	4.0 – 12.5mm	1500-2500 RPM	30.0 – 50.0mm
BMWD5.5-110-5	5.5x110mm	Tek 5	50.0mm	4.0 – 12.5mm	1500-2500 RPM	45.0 – 90.0mm
BMWD5.5-135-5	5.5x135mm	Tek 5	50.0mm	4.0 – 12.5mm	1500-2500 RPM	45.0 – 100.0mm

Technical Data

Hardness Rating (Vickers scale)			Unfactored Mechanical Performance			Pullover Performance	
Diameter	Surface Hardness	Core Hardness	Diameter	Tensile Strength	Shear Strength	Diameter	Substrate – 50mm timber
4.8mm	390.0HV	270.0HV	4.8mm	9.8kN	8.2kN	4.8mm	1.6kN
5.5mm	390.0HV	270.0HV	5.5mm	11.6kN	9.8kN	5.5mm	3.0kN

NOTE: The results expressed in the datasheet are taken as mean loads from a range of empirical tests and are ultimate unfactored loads. Each specifier or end user should make his/ her own decision on what safety factors to use relevant to their design application (such as BS 5950, EN 1991, etc).

Errors and Omissions Excepted. This document shall not be reproduced except in full, without written approval of Evolution Fasteners (UK) Ltd. Data in this document relates only to the specific items described therein. This document is provided and published without prejudice, without recourse, non-assumptist, errors and omissions excepted, no assured value, no liability and all rights reserved.

Copyright © 2020 Evolution Fasteners (UK) Ltd. All rights reserved.



Technical Data continued...

Tek 3 range – Unfactored pull out values							
Diameter	Drill point	Steel Thickness					
		1.2mm	1.6mm	2.0mm	2.5mm	3.0mm	4.0mm
4.8mm	Tek 3	1.9kN	2.7kN	3.5kN	4.5kN	5.0kN	6.3kN
5.5mm	Tek 3	2.0kN	2.4kN	3.6kN	4.3kN	5.1kN	6.7kN

Tek 5 range – Unfactored pull out values							
Diameter	Drill point	Steel Thickness					
		4.0mm	5.0mm	6.0mm	8.0mm	10.0mm	12.5mm
5.5mm	Tek 5	4.5kN	5.9kN	7.3kN	8.9kN	10.7kN	11.9kN

ABOUT OUR TESTING

All test results were derived from empirical testing performed by ETAS (Evolution Testing & Analytical Services), a UKAS (United Kingdom Accreditation Service) accredited testing laboratory (Accreditation No. 7485). The following tests were performed to the following standards.

Testing Procedures

Test/ Parameter	Standard/ Method/ Procedure
Ultimate Tensile	ISO 6892-1: 2009 "Metallic materials – tensile testing – Part 1: Method of test at room temperature".
Ultimate Shear	MIL-STD-1312-13 "Military Standard: Fastener test method (Method 13) Double shear test".
Pull Out (Withdrawal Force)	EN 14566: 2009 "Mechanical fasteners for gypsum plasterboard systems. Definitions, requirements and test methods".
Pull Over	EN 14592: 2008 "Timber structures. Dowel type fasteners. Requirements".
Hardness	ISO 650 7-1: 2005 "Metallic materials – Vickers hardness test – Part 1: Test method".
Corrosion Resistance	EN ISO 9227: 2012 "Corrosion tests in artificial atmospheres. Salt spray tests".
Drilling Time Test	EN 14566: 2009 "Mechanical fasteners for gypsum plasterboard systems. Definitions, requirements and test methods".



7485

Laboratory Contact Details

Evolution Testing & Analytical Services

Units 2A & 2B Clyde Gateway Trade Park
Dalmarnock Road
Rutherglen

South Lanarkshire
G73 1AN

T: (0141) 643 4125
F: (0141) 647 5100